

B1
cont.

found to be 0.017. The EPMA chart is shown in Fig. 1. The molding article was stamped out with a cutting machine (manufactured by Dumbbell Co., Ltd.) into a specimen having a length of 125 mm, a width of 6.5 mm and a thickness of 3 mm. An oxygen index of this specimen was measured with an oxygen index system combustion tester (model: ON-1, manufactured by Toyo Rika Kogyo Ltd.) in accordance with JIS-K7201. The oxygen index was found to be 23.--
